



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## DAP® 100% Silicone Rubber Window, Door & Siding Sealant

### PRODUCT DESCRIPTION

DAP® 100% SILICONE RUBBER WINDOW, DOOR & SIDING SEALANT is a durable, 100% waterproof and weatherproof sealant for sealing out drafts, water and moisture around windows, doors, siding, gutters, flashing, pipes, vents and more. It stays flexible to withstand expansion and contraction without cracking or losing adhesion. Cured sealant is mold and mildew resistant. Interior/exterior use.



PACKAGING	COLOR	UPC
2.8 fl oz (82.8 mL)	White	7079800752
2.8 fl oz (82.8 mL)	Clear	7079800753
9.8 fl oz (289 mL)	White	7079808646
9.8 fl oz (289 mL)	Clear	7079808641
9.8 fl oz (289 mL)	Almond	7079808649
9.8 fl oz (289 mL)	Aluminum	7079808643
9.8 fl oz (289 mL)	Bronze	7079808647
9.8 fl oz (289 mL)	Black	7079808642

### KEY FEATURES & BENEFITS

- When tested in accordance with ASTM C719 meets the ASTM C920 requirements for Class 25, Use G
- 100% waterproof & weatherproof seal
- Flexible
- Cured sealant is mold & mildew resistant
- Interior/exterior use



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

## SUGGESTED USES

### USE FOR CAULKING & SEALING:

- Windows
- Doors
- Siding
- Trim
- Pipes
- Vents
- Ducts
- Gutters
- Flashing

### ADHERES TO:

- Wood
- Composite wood
- Aluminum
- Most metals\*
- Glass
- Ceramic
- Porcelain
- Vinyl
- Most plastics & rubbers
- Most rubbers

## FOR BEST RESULTS

- Apply when surface temperatures are between -35°F to 140°F.
- Joint width should not exceed 1/2". If joint depth exceeds 1/2", use foam backer rod.
- Allow 24 hours for sealant to fully cure. Sealant will not cure in totally confined spaces.
- Not recommended for continuous underwater use, filling butt joints, surface defects, tuck-pointing, chimneys, stovepipes or fireplace applications. Not recommended for structural glazing.
- Corrodes some metals. \*Not recommended for use on or near brass, copper or copper alloys, zinc, iron, galvanized metals or other surfaces prone to attack by weak acids.
- Not for oily woods or cementitious surfaces. Substrates made of methylmethacrylate, polycarbonate, polypropylene, polyethylene and polytetrafluoroethylene do not allow for best adhesion and compatibility with sealant. Try test area before using.
- **Not paintable.** Paint substrate surface before applying sealant.
- Store below 80°F in dry place for optimal shelf life.

## APPLICATION

### Surface Preparation

Surface must be clean, dry, structurally sound and free of old caulk, dirt, dust & other foreign material.

### Product Application

1. If using squeeze tube, remove cap & cut nozzle at 45° angle to desired bead size. Unscrew nozzle & remove foil seal. Replace nozzle.
2. If using cartridge, cut nozzle at a 45° angle to desired bead size. Puncture inner foil seal. Load into caulk gun.
3. Fill gap or crack with sealant.
4. If necessary, tool or smooth the bead of sealant with a finishing tool before the sealant skins over.
5. Allow sealant to cure for at least 12 hours before exposing to water.



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

6. Do not touch or clean sealant for 24 hours. Sealant reaches full cure in 24 hours.
7. Clean up excess uncured sealant from surface and tools with mineral spirits. Scrape or cut away excess cured sealant. Do not use mineral spirits to clean hands or skin. Wash hands or skin with soap and water.
8. Sealant is not paintable. Paint surfaces prior to applying sealant.
9. Reseal cartridge/tube for storage and reuse.

## TYPICAL PHYSICAL & CHEMICAL PROPERTIES

<b>Typical Uncured Physical Properties</b>	
Appearance/Consistency	Smooth, gunnable paste
Base Polymer	Silicone rubber
Filler	Not applicable
Volatile	Not applicable
Weight % Solids	>97%
Density (lbs per gallon)	8.0
Odor	Vinegar like
Clean Up	Mineral spirits
Flash Point	>212°F
Freeze Thaw Stability (ASTM C1183)	Will not freeze
Shelf Life	24 months
Coverage	9.8 oz: 53 linear feet at 3/16" diameter bead 2.8 oz: 15 linear feet at 3/16" diameter bead
<b>Typical Application Properties</b>	
Application Temperature Range	-35°F to 140°F
Tooling Time (Working Time)	5-10 minutes
Tack Free Time	10-20 minutes
Full Cure	24 hours
Return to Service Time	12 hours
Vertical Sag (ASTM D2202)	0.05"
<b>Typical Cured Performance Properties</b>	
Service Temperature Range	-40°F to 350°F continuous use, up to 400°F intermittent use after full cure
Water Ready Time	12 hours
Paint Ready Time	Not paintable



# TECHNICAL DATA SHEET

2400 Boston Street | Suite 200 | Baltimore, MD | 21224

Mildew Resistance	Cured sealant is mold & mildew resistant
Dynamic Joint Movement (ASTM C719)	+/-25%

## CLEAN UP & STORAGE

Remove excess uncured sealant from surfaces and tools with mineral spirits. Excess cured sealant must be cut or scraped away. Do not use mineral spirits to clean hands or skin. Wash hands or skin with soap and water. Store container in temperatures below 80°F and in a dry place.

## SAFETY

See product label or Safety Data Sheet (SDS) for health and safety information. You can request a SDS by visiting our website at [dap.com](http://dap.com) or calling 888-DAP-TIPS.

## WARRANTY

**WARRANTY:** If product fails to perform when used as directed, within one year of date of purchase, call 888-DAP-TIPS, with your sales receipt and product container available, for replacement product or sales price refund. DAP Products Inc. will not be responsible for incidental or consequential damages.

## COMPANY IDENTIFICATION

**Manufactured for:** DAP Products Inc., 2400 Boston Street, Baltimore, Maryland 21224

**Usage Information:** Call 888-DAP-TIPS or visit [dap.com](http://dap.com) & click on "Ask the Expert"

**Order Information:** 800-327-3339 or [orders@dap.com](mailto:orders@dap.com)

**Fax Number:** 410-558-1068

**Also, visit the DAP website at [dap.com](http://dap.com)**